

# Optimization of wear protective DLC coatings by use of nanoindentation and Raman spectroscopy.

K. Pagh Almtoft<sup>a</sup>, S. Sønderby<sup>b</sup>, A. Nørlov Berthelsen<sup>b</sup>, L. Pleth Nielsen<sup>a</sup>, J. Bøttiger<sup>b</sup>

<sup>a</sup>Tribology Centre, Danish Technological Institute, DK-8000 Aarhus C, Denmark

<sup>b</sup>Interdisciplinary Nanoscience Center (iNANO) and Department of Physics and astronomy, University of Aarhus, DK-8000 Aarhus C, Denmark

## **Abstract**

Hydrogen-containing DLC (a-C:H) coatings have been deposited by magnetron sputtering in an industrial setup equipped with graphite targets and the sputtering gas containing acetylene. To obtain optimum wear resistance, the C<sub>2</sub>H<sub>2</sub> gas flow and the substrate bias voltage were systematically varied. The coating properties were characterized by nanoindentation, Rockwell C indentations and Raman spectroscopy. The nanoindentation yielded the hardness H and the Young's modulus E, and from the maximum H/E ratio the optimum wear resistance was found. The Rockwell C indentations characterized the adhesion qualitatively, and the Raman spectroscopy revealed the stress, the hydrogen content and the sp<sup>3</sup>/sp<sup>2</sup> ratio. The hardness was found to be close to proportional to the stress. To improve the adhesion the stress was lowered – without lowering the hardness significantly – by annealing the coatings and/or doping with Cr, the latter introducing nanocrystalline carbide grains.

Preferred type of presentation: Oral